



US CONSTRUCTION FABRICS LLC

8 Ledge Rd, Windham, NH 03087

(603) 893-5480, Fax (603) 893-2154

www.usconstructionfabrics.com

Wholesale Distribution

CONSTRUCTION FABRICS, LINERS, & ENVIRONMENTAL PRODUCTS

40 mil PVC Geomembrane Specifications

TYPICAL APPLICATIONS:

Landfill Liners

Landfill Closures

Reservoirs

Sewage Lagoons

Soil Remediation

Industrial Waste Ponds

PVC liners are a single-ply construction fabrication with Polyvinyl Chloride as the principle polymer. Only first quality virgin resins are used and all materials meet or exceed the requirements of ASTM D7176 Standard Specification for PVC geomembranes used in buried applications.

We utilizes statistical process control (SPC) to ensure the integrity of each panel produced. Samples from actual factory seams are removed during the welding process for a rigorous, proven testing procedure that assures you of the highest quality factory-fabricated PVC geomembranes available.

PVC Liners are fabricated in panels, accordion-folded in both directions, and packaged for shipment to your site for quick, easy installation to save you time and money.

Thickness \pm 5%	ASTM D-5199	.040"
Specific Gravity (min)	ASTM D-792	1.20
Tensile (lb/in-width, min)	ASTM D-882	97
Elongation at Break (% min)	ASTM D-882	430
Modulus (lb/in-width, min)	ASTM D-882	40
Tear Resistance (lb/in, min)	ASTM D-1004	10
Resistance to Soil Burial (% change, max)	ASTM G-160	
1. Breaking Factor		5
2. Elongation At Break		20
3. Modulus at 100% Elongation		20
Impact Cold Crack ($^{\circ}$ C)	ASTM D-1790	-29
Dimensional Stability (% change, max)	ASTM D-1204 (212 $^{\circ}$ F/15 min.)	3
Water Extraction (% max)	ASTM D-1239	0.20
Volatile Loss (% max)	ASTM D-1203(A)	0.50
Hydrostatic Resistance (psi, min)	ASTM D-751(A)	120
Plasticizer Min Ave Molec Wt	ASTM 2124	400
Factory Fabricated Seams:		
Peel Strength (lbs/in, min)	ASTM D-882	15
Shear Strength (lbs/in, min)	ASTM D-882	77.6

These data are based on tests believed to be reliable. However, these are laboratory tests that may not simulate actual use conditions. They are provided for your informational purposes only. No warranty, express or implied, including any other further warranty of fitness for a particular purpose or merchantability, is made by this promotional literature.