



US CONSTRUCTION FABRICS LLC

8 Ledge Rd, Windham, NH 03087

(603) 893-5480, Fax (603) 893-2154

www.usconstructionfabrics.com

CONSTRUCTION FABRICS, LINERS, & ENVIRONMENTAL PRODUCTS



Geotextile Product Description Sheet

SKAPS GT-135 Nonwoven Geotextile

SKAPS GT-135 is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. SKAPS GT-135 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. SKAPS GT-135 conforms to the physical property values listed below:

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Weight (Typical)	ASTM D 5261	oz/yd ² (g/m ²)	3.5 (119)
Grab Tensile	ASTM D 4632	lbs (kN)	90 (0.401)
Grab Elongation	ASTM D 4632	%	50
Trapezoid Tear Strength	ASTM D 4533	lbs (kN)	40 (0.178)
CBR Puncture Resistance	ASTM D 6241	lbs (kN)	265 (1.18)
Permittivity*	ASTM D 4491	sec ⁻¹	2.0
Water Flow*	ASTM D 4491	gpm/ft ² (l/min/m ²)	150 (6095)
AOS*	ASTM D 4751	US Sieve (mm)	50(0.3)
UV Resistance	ASTM D 4355	%/hrs	70/500

PACKAGING	
Roll Dimensions (W x L) – ft	12.5/15 x 360
Square Yards Per Roll	500/600
Estimated Roll Weight – lbs	130/155

* At the time of manufacturing. Handling may change these properties.

This information is provided for reference purposes only and is not intended as a warranty or guarantee. SKAPS assumes no liability in connection with the use of this information.

Made in U.S.A.