

Eterna-Seal
ELASTOMERIC
FLASHING CEMENT
7174



PHYSICAL PROPERTIES :

Eterna-Seal Elastomeric Flashing Cement was formulated in conjunction with Eterna-Seal Roof Coatings. It forms a base for stacks, parapet walls, curbs and other vertical to horizontal roof transitions. It is typical used in tandem with reinforcing fabric, and is formulated to be compatible with most existing roof systems. It can also be used as a base to repair irregular, alligatored surfaces prior to topcoating with Eterna-Seal field coatings. Refer to published guide specifications for additional details.

SPECIFICATIONS

| | |
|--|-------------------|
| Flash Point | 105°F |
| % Solids | 60 ± 2% |
| Application | Trowel |
| Film Thickness of 1 gallon | 10 mils, 100sq.ft |
| Elongation at 72°F | 400% Min. |
| Recovery from 400% Elongation | 90% |
| 100% Elongation | 100% |
| Temperature Range | -30° to 200°F |
| Application Range | 40° to 100°F |
| Dry to touch | 4 to 24 hours |
| Dry throughout | 30 days |
| Total Cure Time | 45 to 60 days |
| Tensile Strength | 600 psi min. |
| Compatibility with old asphalt built-up roof | Excellent |
| Weight/gallon | 9.2 lbs. |
| Viscosity | Heavy paste |
| Moisture Vapor Transmission, Perms | .15 |

7174