

PHYSICAL PROPERTIES :

Leak Patch is a product formulated with specially refined asphalt and plasticizers reinforced with carefully selected fiber which gives it a soft and pliable characteristic for years. Refer to published guide specifications for additional details.

SPECIFICATIONS

Flash Point (ASTM D93)	103°F Min.
Weight/Gallon (Approximate)	9 lbs.
Viscosity @ 80°F (ASTM D217)	270-330 KU
Non-Volatile (Fed. Test Method 141)	70% Min.
% of Specially Processed Bitumen	30% Min.
% of Total Solids, by Volume	70% Min.
Film Thickness Dry of 1 gal./15 sq. ft.	75 mils
Drying Time	2-3 Days
Service Temperature, extended exposure	-20 - 150°F
Resistance to Oils & Solvents	Poor
Resistance to Sunlight	Good
Resistance to Chemicals	Good
Effect of Weathering	Slight Chalking
Water Resistance (under good drainage conditions)	Excellent
Water Resistance (under continuous submersion)	Fair
Approximate Coverage per Gallon	15 sq. ft.
Shipping Weights	
5 gal. pail	48 lbs.
1 gal cans (4/case)	40 lbs.
Solvent for Clean-Up	Naptha

6229