



NextGen Eterna-Seal® Non-Fibered Rubber Roof Coating

7114 NF

Rubber Roof Coating – Metal Top Coat

Revision: 02/2023

TYPICAL PHYSICAL PROPERTIES

COLOR	WHITE
COVERAGE RATE	65 – 100 SF/GAL
WEIGHT	8.6 LBS/GAL
SOLIDS (% BY WEIGHT)	51.0 ± 1%
DRYING TIME	2 – 4 HOURS
VISCOSITY @ 78°F	4100 CP
ELONGATION	400%
TENSILE STRENGTH.....	ASTM D-412...1500 PSI

RECOMMENDED SPRAY EQUIPMENT: AIRLESS

TIP SIZE	0.025” – 0.035”
FLUID PRESSURE (PSI).....	3000
FLUID HOSE SIZE	3/8” – 1/2”

Metal building owners have a wide variety of roofing systems to choose from but few have been designed specifically for the restoration and maintenance of metal roofs. Instead, traditional roofing materials have been forced to conform with the unique requirements of the metal substrate. Aesthetic considerations aside, asphalt coatings are too brittle to bridge thermal-induced movement along seams, end laps, fastener heads and roof protrusions. While single-ply systems provide a durable membrane, these materials were not designed for use over corrugated, irregular surfaces.

PRODUCT DESCRIPTION

TRUCO’s 7114 NF NextGen Eterna-Seal® Non-Fibered Rubber Roof Coating is a high-value Top Coat, to pair with TRUCO’s 7145 NF Metal Base Coat on Metal Roof applications! This Top Coat provides excellent waterproofing and ultraviolet resistance by creating a flexible, seamless membrane. 7114NF was specifically formulated as a Metal Top Coat with its excellent intercoat adhesion to the 7145 NF Metal Base Coat, bright white color, and high performing UV package. It is thermally stable and resists cracking and peeling due to weather extremes. Other properties include high tensile strength, chemical resistance and low water vapor permeability.

SURFACE PREPARATION:

The surface must be free of any oils, moisture, soil or other contaminants that may interfere with good adhesion. Remove any loose material from seams or other surfaces. Oil and grease should also be removed with solvents or an appropriate detergent cleaner such as TRUCO’s 300

Cleaner/Degreaser. In many cases, high pressure water blast will be sufficient to prepare the surface.

APPLICATION INSTRUCTIONS:

TRUCO’s 7114 NF may be applied by medium nap rollers, soft brushes or high pressure airless spray equipment. Apply 7114 NF only to clean, dry, sound surfaces free of loose particles or other foreign matter. For best results, substrate temperature should be between 50 – 100°F. For best spray application, the product should be at a minimum of 70°F. Sudden temperature declines may result in dew formation on surfaces, which can prevent adhesion development.

LIMITATIONS AND PRECAUTIONS:

7114NF contains a blend of solvents which is considered combustible by D.O.T. and O.S.H.A. standards. It should be used and stored away from heat, flames and sources of ignition in a well-ventilated atmosphere. Avoid contamination in sealed containers. Do not inhale vapor or mist; do not get on skin, in eyes or on clothing. Refer to SDS for more information.

The specifications, properties and performance of materials described herein are based on information believed to be reliable. Unless otherwise expressly provided in written contract, the products discussed are sold without conditions or warranties, expressed or implied. Product specifications are subject to change without notice.