

Complexity, involved, and intricate are easy. Simplicity is hard. Rib It makes it look simple but features a number of thoughtful executions, making advanced design and installation simple. Each channel is beveled on all sides for more seamless panel-to-panel mating, the rhythmic lines create more perceptual space, in-field trimming takes seconds, and our new Feltware install system reduces the need for hardware.

## Specifying Acoustics never Felt better.

Bringing our legendary innovation, attention to detail, speed, service, and value to PET felt.



### **Specifications**

Product Name	Rib It
Content	100% Polyester (PET) with a minimum of 60% recycled content
Felt Thickness	12mm
Size	24" x 48" x 2"
Weight	.75/lbs per sq ft
Edge Options	Exposed felt
Sound Performance	ASTM C423-17: NRC = 0.75
Fire Performance	Product made from Class A PET felt material tested under ASTM-84
Variations	Sonus Felt uses an industry standard felting process. Slight and consistent variations in color and "heathering" should be expected when using this sustainable material. Slight imperfections are within normal manufacturing tolerance and not visible in standard installations.
Maintenance	Vacuum to remove any loose dirt or dust. You may use a soft or plastic bristle brush to loosen it. Avoid excess pressure. Compressed air can also be used to dust the material in difficult or large installations. If stains are present, you may saturate a lint-free cloth with a mild detergent or soap and water solution.
Warranty	10 years
Unit of Sale	Per Unit

### **Price**




Snap the QR Code or visit sonusna.com to see pricing.


Sonus is the only manufacturer to have published universal pricing because:


- We got nothing to hide.
  We are here for you: faster, easier, straightforward.

Sonus creates the perfect experience for each person in any moment.

# Design & Installation










### **Colors**



### **Test Results**



Freq (Hz)	Absorption Coefficiency
160	0.33
250	0.30
500	0.60
800	1.03
1000	1.10
2000	1.20
3150	1.08
NRC	0.80

The Noise Reduction Coefficiency (NRC) is calculated as the arithmetic average of the absorption coefficients in the shaded bands only (250,500, 1250 & 2000 Hz).

ASTM C 423-17: Type F20 Mounting - Tested specimen mounted with Z bar and designed airspace behind it to simulate a standard wall installation.