
Artificial Solid Electrolyte Interphase for Suppressing Surface Reactions and Cathode Dissolution in Aqueous Zinc Ion Batteries

Jing Guo,[†]
[®] Jun Ming,[†]
[®] Yongjiu Lei,[†] Wenli Zhang,[†]
[®] Chuan Xia,[†]
[®] Yi Cui,*,^{‡,§}
[®] and Husam N. Alshareef*,†60

Supporting Information

Downloaded via KING ABDULLAH UNIV SCI TECHLGY on March 22, 2021 at 13:53:53 (UTC). See https://pubs.acs.org/sharingguidelines for options on how to legitimately share published articles.

ABSTRACT: Vanadium-based compounds have been widely used as electrode materials in aqueous zinc ion batteries (ZIBs) due to the multiple oxidation states of vanadium and their open framework structure. However, the solubility of vanadium in aqueous electrolytes and the formation of byproducts during the charge/discharge process cause severe capacity fading and limit cycle life. Here, we report an ultrathin HfO2 film as an artificial solid electrolyte interphase (SEI) that is uniformly and conformally deposited by atomic layer deposition (ALD). The inactive hafnium(IV) oxide (HfO₂) film not only decreases byproduct $(Zn_4SO_4(OH)_6\cdot xH_2O)$ formation on the surface of Zn₃V₂O₇(OH)₂·2H₂O (ZVO) but also suppresses the ZVO cathode dissolution in the electrolyte. As a result, the obtained HfO2-coated ZVO cathodes deliver higher



capacity and better cycle life (227 mAh g⁻¹@100 mA g⁻¹, 90% retention over 100 cycles) compared with pristine ZVO (170 mAh g⁻¹@100 mA g⁻¹, 45% retention over 100 cycles). A mechanistic investigation of the role of HfO₂ is presented, along with data showing that our method constitutes a general strategy for other cathodes to enhance their performance in aqueous ZIBs.

 \P he lithium-ion battery (LIB) is the most important energy storage technology, which has been widely employed in various applications. However, current commercial LIBs have some limitations such as flammable electrolyte, limited lithium supplies, and high cost.¹⁻⁴ These issues have motivated the search for alternative battery technologies such as rechargeable aqueous batteries. Compared with organic electrolytes, water-based electrolytes show high ionic conductivity (~1 S cm⁻¹), simple processing, and good safety. 5-9 Among the various aqueous batteries, rechargeable aqueous zinc ion batteries (RAZIBs) exhibit great promise due to zinc having a low redox potential (-0.762)V vs SHE), high theoretical capacity (819 mAh g⁻¹, 5851 mAh mL⁻¹), great earth abundance, and ease of material handling 10-16 handling.

To date, various materials have been reported as the cathode for RAZIBs (e.g., MnO₂, Prussian blue analogues, polyanion Among them, vanadium-based compounds compounds).17with an open framework structure possess higher energy

density than other cathodes, which can be attributed to the multiple oxidation states of vanadium and their stable layered structure. 21,22 Despite these advantages, vanadium-based compounds still suffer from fast capacity fading, but the reason remains unclear. The formation of an inactive byproduct has been detected on the surface vanadium-based cathodes during the discharge process in previous works, an effect that was attributed to the reaction between OH and ZnSO4 during the proton co-insertion process.^{23,24} Unfortunately, this insulating byproduct impedes the electrochemical reaction and causes increased resistance during repetitive cycling. The formation of Zn₄SO₄(OH)₆·xH₂O covers the cathode surface, leading to a decrease of electrochemically active surface area and hindering the movement of the electrons. In addition, vanadium-based cathodes are likely to dissolve in neutral/mildly acidic

Received: September 16, 2019 Accepted: October 23, 2019 Published: October 23, 2019



 $^{^\}dagger$ Materials Science and Engineering, Physical Science and Engineering Division, King Abdullah University of Science and Technology (KAUST), Thuwal 23955-6900, Saudi Arabia

[‡]Department of Materials Science and Engineering, Stanford University, Stanford, California 94305, United States

[§]Stanford Institute for Materials and Energy Sciences SLAC National Accelerator Laboratory, Menlo Park, California 94025, United

electrolytes, as has been previously reported. 25,26 The solubility of vanadium-based materials leads to direct capacity fading with cycling via loss of cathode active materials. Several approaches have been attempted to overcome these drawbacks. Chen et al. developed a mixed aqueous electrolyte consisting of both Na₂SO₄ and ZnSO₄, which effectively inhibited the continuous dissolution of NaV₃O₈·1.5H₂O.²⁴ Na₂SO₄ as an additive in the electrolyte not only changed the dissolution equilibrium between the electrode and electrolyte but also suppressed Zn dendrite growth. Therefore, a good reversible capacity (380 mAh g^{-1} @100 mA g^{-1}) and enhanced long-term cycling performance (82% over 1000 cycles) were achieved for RAZIBs. Hu et al. deposited PEDOT with 5 nm thickness as a protective layer on the surface of V2O5 nanosheets, which improved zinc storage performance and promoted zinc ion and electron transport kinetics.²⁷ This hybrid PEDOT/V₂O₅ electrode exhibited a specific capacity up to 232 mAh g⁻¹ at a large current density of 20 A g⁻¹ and excellent cycle life (97% retention after 600 cycles at 1 A g⁻¹ and 89% after 1000

Atomic layer deposition (ALD) is an effective method to coat uniform and conformal layers on complex and high-area surface structures via a sequential self-limiting gas/solid reaction. The thickness of the ALD coating can be easily tailored at the atomic scale. ALD coatings of TiO₂, ToO₂, and HfO₂, have been proposed as surface passivation layers to improve the performance of LIB. The undesirable interfacial reactions between the electrodes and electrolytes could be effectively suppressed by using a passivating ALD layer. This passivation layer acts as an artificial solid electrolyte interphase (SEI) in the rechargeable aqueous battery, which is important in determining the electrochemical performance of the electrode. To the best of our knowledge, using ALD surface engineering to improve zinc ion storage performance has not been reported.

Here, we demonstrate that HfO_2 -coated $Zn_3V_2O_7(OH)_2$ · $2H_2O$ (denoted as HfO_2 -coated ZVO) effectively prevents cathode dissolution during cycling and largely decreases the formation of the insulating side products $(Zn_4SO_4(OH)_6\cdot xH_2O)$ at the electrode/electrolyte interface. As a result, a functional RAZIB with a HfO_2 -coated surface of the ZVO cathode delivers higher specific capacity and better long-term cycling ability compared with the pristine ZVO.

The process of preparation for a self-standing HfO₂-coated ZVO electrode could be divided into two steps, as illustrated in Figure 1. First, ZVO nanobelts are prepared by microwave synthesis and dispersed into deionized water with Super P binder (carboxymethylcellulose (CMC) and styrene-butadiene rubber (SBR)) to form a homogeneous dispersion (see details in the Experimental Section in the Supporting Information). The mixture is assembled by a facile vacuum filtration system, yielding a film that could be easily peeled off from filter membranes to form a free-standing ZVO electrode. In the second step, the as-obtained electrodes are transferred into the ALD system for HfO2 surface deposition on ZVO at 180 °C. To decrease the inner resistance, HfO₂ is directly deposited on the assembled electrode instead of individual nanobelts followed by electrode making. Our way maintains direct interparticle electronic pathways without crossing the insulating HfO2 layer while HfO2 helps in "gluing" particles together. 33 The thickness of the HfO2 coating layer is simply controlled by the number of deposition cycles. After the ALD




Figure 1. Schematic illustration of the fabrication process of a pristine ZVO cathode and the HfO₂-coated ZVO by ALD. The ALD coating acts as an artificial solid interphase layer, which significantly improves the performance and stability of the ZIB cathodes.

process, the morphology of the HfO-coated ZVO cathode is retained (Figure S1).

The crystal structure of pristine ZVO and HfO2-coated ZVO cathodes was studied by X-ray diffraction (XRD). All of the diffraction peaks obtained for both samples are indexed as $Zn_3V_2O_7(OH)_2\cdot 2H_2O$ (JCPDS No. 50-0570) with no signs of impurity phases (Figure 2a). No different peaks corresponding to HfO2 could be observed in the XRD pattern, which is most likely due to its 5 nm thickness and amorphous state.³⁴ The chemical composition and bonding state of the HfO2-coated ZVO cathode were evaluated by X-ray photoelectron spectroscopy (XPS). The high-resolution spectrum of V 2p is shown in Figure 2b. The peaks at 517.3 and 524.6 eV can be ascribed to the V $2p_{3/2}$ and V $2p_{1/2}$ peaks of V⁵⁺, which demonstrate that the chemical valence of vanadium has not been affected by the HfO_2 coating.³⁵ The peaks around 17.0 and 18.7 eV of the Hf 4f spectrum in Figure 2c are related to $4f_{7/2}$ and $4f_{5/2}$ respectively, which belong to the Hf–O bonding in HfO₂. ³⁶ The XPS data on Zn and O (Figure S2a,b) exhibit signals that can be expected for the sample of HfO2coated ZVO, which matches well with the previous report for pure ZVO. Transmission electron microscopy (TEM), high angle annular dark-field scanning TEM (HAADF-STEM), and high-resolution TEM (HRTEM) were employed to provide structural information on the samples. As shown in Figure 2d, a clear interface between the core and shell is easily observed, which is related to the different atomic numbers of the atoms present in these two regions. In Figure 2e, a uniform HfO2 layer with a thickness of 5 nm can be seen maintaining a welldefined nanobelt morphology with a core-shell structure compared with pristine ZVO (Figure S3). The lattice spacing of 0.21 nm is observed in Figure 2f, which corresponds to the interplanar spacing of ZVO(022) planes. Elemental mapping was performed using energy dispersive X-ray spectroscopy (EDS), as shown in Figure 2g--k. The Zn, V, O, and Hf elements are homogeneously distributed in the HfO2-coated ZVO nanobelts. These results demonstrate that the ultrathin HfO₂ layer has been successfully deposited on the surface of a ZVO free-standing electrode film.

The electrodes made by vacuum filtration were used as cathodes in aqueous ZIBs, where zinc foil and 1 M ZnSO₄ were used as the anode and electrolyte, respectively. Figure 3a shows the cyclic voltammetry (CV) plot obtained at a scan rate of 0.3 mV s⁻¹ in the voltage window of 0.2–1.8 V (vs Zn/




Figure 2. Morphology and structure of as-prepared HfO₂-coated ZVO and pristine ZVO cathodes. (a) XRD pattern showing that the HfO₂ coating does not change the ZVO cathode structure. (b,c) XPS high-resolution spectra of (b) V 2p and (c) Hf 4f obtained from HfO₂-coated ZVO. (d) HAADF-STEM image, (e) TEM image, and (f) HRTEM image of HfO₂-coated ZVO. (g-k) TEM-EDS elemental maps of a HfO₂-coated ZVO individual nanobelt.

Zn²⁺). The shape of the CV curves is similar for the two samples, indicating that the HfO2 layer does not significantly change the electrochemical reaction during Zn²⁺ de/ intercalation. The RAZIBs with a HfO2-coated ZVO cathode deliver a smaller polarization than pristine ZVO, which implies faster kinetics. To further understand the charge storage kinetics of these hosts, the diffusion-controlled and capacitive contributions were quantitatively determined from CV curves measured at different scan rates (Figure S4a,b), and the bvalues of six peaks were calculated (Figure 3b). The b values of HfO₂-coated ZVO were 0.74, 0.98, 0.8, 0.77, 0.67, and 0.84, corresponding to peaks labeled as A1, A2, A3, C1, C2, C3 (Figure 3a), respectively. The b values for the HfO₂-coated ZVO are higher than those of pristine ZVO, suggesting enhanced reaction kinetics.^{37,38} The contribution ratio of capacitive response to the whole capacity of HfO2-coated ZVO at a scan rate of 0.3 mV s⁻¹ is 76.6%, indicating pseudocapacitance-controlled electrochemical reactions (Figure S5). The rate performance is presented in Figure 3c, where the current density increases from 100 to 3000 mA g⁻¹ and then back to 500 mA g⁻¹. The reversible discharge capacities of HfO₂-coated ZVO cathodes are 215, 190, 165, 120, 106, and 88 mAh g^{-1} at 100, 300, 500, 800, 1000, and 3000 mA g^{-1} , respectively. When the current density is reduced to 500 mA g⁻¹, an average discharge capacity of 162 mAh g⁻¹ can be recovered. At a low current density of 100 mA g⁻¹ in Figure 3d, the HfO₂-coated ZVO delivers 227 mAh g⁻¹ and 90% capacity

retention after 100 cycles. However, ZVO delivers a lower initial capacity, and only 45% is retained after the same number of cycles, indicating rapid capacity degradation. To gain insight into the reason for the fast capacity fading in pristine ZVO, ICP-OES was conducted to determine the electrolyte composition during cycling (herein, a three-electrode electrolyzer was used to collect the electrolyte). As shown in Figure 3e, the electrode was immersed in the electrolyte for 2 h before testing. The vanadium detected in the electrolyte before electrochemical testing should be ascribed to the dissolved cathode material. The concentration of vanadium in the case of pristine ZVO increases with cycling, indicating that the vanadium corrosion becomes more serious due to the direct contact between the active material and the mild acidic electrolyte (pH = 5.1). In comparison, the HfO₂-coated ZVO cathode has much less vanadium dissolution, which is consistent with the better performance at low current density. As a general method, the artificial solid interphase can be applied for other materials (Figure S6). Even at a high rate of 10 A g⁻¹ (Figure 3f), 84% of the original capacity has been retained after 1000 cycles for HfO2-coated ZVO cathodes, which shows excellent long-term durability with negligible capacity decay compared to the pristine ZVO electrode cathode (only 70% of the capacity is retained).

In order to get further information on the energy storage mechanism, ex situ XRD and electrochemical impedance spectroscopy (EIS) experiments were carried out to analyze




Figure 3. Electrochemical performance of the HfO₂-coated ZVO and pristine ZVO cathodes: (a) CV curves measured at a scan rate of 0.3 mV s⁻¹; (b) b value for different redox peaks determined from the $\log(i)$ versus $\log(v)$ plots; (c) rate performance; (d) cycling performance at a current density of 100 mA g⁻¹; (e) ICP-OES results after different numbers of cycles; (f) cycling performance at a current density of 10 A g⁻¹.

the pristine ZVO and HfO2-coated ZVO electrode during the charge/discharge process. As marked in Figure 4a, in the ex situ XRD pattern of ZVO, upon deep charge to 0.2 V in the third cycle, the peak located at 24.7° corresponding to (002) reflection shifts to a lower angle, which is caused by the coinsertion of H₂O and Zn²⁺. In the subsequent discharge process, the (002) reflection shifts back to its initial position due to the Zn2+ deintercalation, which indicates a reversible reaction related to Zn²⁺ uptake/removal from the ZVO lattice. Most interestingly, apart from the peak shifting, a new group of peaks can be observed in the XRD pattern of ZVO. The peaks that appear at 26, 27.6, and 28.8° are well assigned to $Zn_4SO_4(OH)_6\cdot xH_2O$, which is an insulating byproduct reported in previous literature.³⁹ The Zn₄SO₄(OH)₆·xH₂O continuously formed with decreasing voltage and gradually diminished upon voltage reversal. The same phenomenon has also been found in previous work.²⁴ The reversible formation of Zn₄SO₄(OH)₆·xH₂O should be ascribed to the reaction between ZVO and electrolyte, which results in an insulating layer deposited on the cathode surface (Figure S7). It should be noted that this byproduct can significantly influence the electrochemical reaction during the discharge process, and this point can also be proved by the ex situ EIS measurement (Figure S8). The charge transfer resistance (R_{ct}) of the two samples at different charge/discharge stages in the first cycle are shown in Figure 4b,c. Figure 4b shows that R_{ct} increases sharply during the discharge process (from 24.8 to 304.9 Ω) and reverts to near the original value (from 304.8 to 15.4 Ω) in the charging process. Dramatic changes take place in R_{ct} during the whole process because the byproducts partly insulate the electrode surface, which leads to an increase in internal resistance and hinders electron transportation. For the HfO₂coated ZVO electrode, the R_{ct} changes more gradually

compared to bare ZVO (Figure 4c). This result can be attributed to the HfO2 layer, which acts as an artificial passive layer, effectively suppressing the Zn₄SO₄(OH)₆·xH₂O formation. It is worth mentioning that the R_{ct} of the HfO₂-coated ZVO electrode is higher than that of pristine ZVO at the initial state, which can be attributed to the low conductivity of HfO₂. On the basis of these findings, we proposed the storage mechanism shown in Figure 4d,e. During the discharge process, OH reacts with ZnSO₄, resulting in a large amount of $Zn_4SO_4(OH)_6$: xH_2O formation on the ZVO surface (Figure 4d). $Zn_4SO_4(OH)_6 \cdot xH_2O$ as an insulating byproduct not only increases the internal resistance of the whole battery but also seriously impedes the reactions by decreasing the electrochemically active area during cyclings.²³ It will be detrimental to power capability and extended cycling. An ultrathin HfO₂ layer deposited by the ALD approach can directly separate the electrode and electrolyte. On the one hand, formation of the byproduct could be effectively suppressed due to the different properties of the interface, which leads to a higher capacity. On the other hand, the contact between the cathode and electrolyte is avoided by the HfO2 layer, alleviating the dissolution of active material. Meanwhile, the Zn2+ could transport through the interface quickly, indicating that the Zn²⁺ diffusion kinetics are not affected by the passive layer because of the amorphous state of the HfO2 layer.

In conclusion, we have shown that the surface passivation of ZVO cathodes by HfO₂ as an artificial SEI significantly enhances the performance of ZIBs. When compared with pristine ZVO, the HfO₂-coated ZVO cathode exhibits largely enhanced capacity and cycling stability. The mechanism of capacity fading has been studied, which demonstrates that the artificial SEI HfO₂ layer plays a bifunctional role during the cycling process. It works as a screen that isolates the electrode




Figure 4. (a) XRD characterization of the ZVO cathode during the charging and discharging process. The charge transfer resistance of (b) uncoated ZVO and (c) HfO₂-coated ZVO during the charge and discharge process. A more gradual change in the charge transfer resistance is seen in the case of HfO₂-coated ZVO. Schematic illustration of the RAZIB storage mechanism with (d) ZVO and (e) the HfO₂-coated ZVO cathodes. Colors: blue, dissolved V ions; gold, Zn.

and electrolyte, reducing dissolution of active materials in the electrolyte and suppressing the formation of the insulating byproduct. This approach was demonstrated to work with other cathode materials, which shows the universality of our artificial SEI approach.

■ ASSOCIATED CONTENT

S Supporting Information

The Supporting Information is available free of charge on the ACS Publications website at DOI: 10.1021/acsenergy-lett.9b02029.

Experimental details, SEM images, XPS spectra, TEM and HRTEM images, CV curves, contribution ratio of the capacitive-controlled charge, XRD results, cycling performance, EIS results, and equivalent circuit models (PDF)

AUTHOR INFORMATION

Corresponding Authors

*E-mail: yicui@stanford.edu.

*E-mail: Husam.alshareef@kaust.edu.sa.

ORCID ®

Jing Guo: 0000-0001-9539-4353 Jun Ming: 0000-0001-9561-5718 Wenli Zhang: 0000-0002-6781-2826 Chuan Xia: 0000-0003-4526-159X Yi Cui: 0000-0002-6103-6352

Husam N. Alshareef: 0000-0001-5029-2142

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

The research reported in this publication is supported by King Abdullah University of Science and Technology (KAUST).

REFERENCES

(1) Dunn, B.; Kamath, H.; Tarascon, J.-M. Electrical energy storage for the grid: a battery of choices. *Science* **2011**, 334 (6058), 928–935. (2) Tarascon, J.-M.; Armand, M. Issues and challenges facing. *Nature* **2001**, 414 (15), 359–367.

(3) Armand, M.; Tarascon, J.-M. Building better batteries. *Nature* **2008**, 451 (7179), 652–657.

- (4) Arico, A. S.; Bruce, P.; Scrosati, B.; Tarascon, J. M.; van Schalkwijk, W. Nanostructured materials for advanced energy conversion and storage devices. *Nat. Mater.* **2005**, *4*, 366–377.
- (5) Pasta, M.; Wessells, C. D.; Huggins, R. A.; Cui, Y. A high-rate and long cycle life aqueous electrolyte battery for grid-scale energy storage. *Nat. Commun.* **2012**, *3*, 1149.
- (6) Wang, G.; Fu, L.; Zhao, N.; Yang, L.; Wu, Y.; Wu, H. An Aqueous Rechargeable Lithium Battery with Good Cycling Performance. *Angew. Chem.* **2007**, *119* (1–2), 299–301.
- (7) Chen, L.; Guo, Z.; Xia, Y.; Wang, Y. High-voltage aqueous battery approaching 3 V using an acidic-alkaline double electrolyte. *Chem. Commun.* **2013**, 49 (22), 2204–2206.
- (8) Yan, J.; Wang, J.; Liu, H.; Bakenov, Z.; Gosselink, D.; Chen, P. Rechargeable hybrid aqueous batteries. *J. Power Sources* **2012**, *216*, 222–226.
- (9) Zuo, W.; Zhu, W.; Zhao, D.; Sun, Y.; Li, Y.; Liu, J.; Lou, X. W. Bismuth oxide: a versatile high-capacity electrode material for rechargeable aqueous metal-ion batteries. *Energy Environ. Sci.* **2016**, 9 (9), 2881–2891.
- (10) Kundu, D.; Adams, B. D.; Duffort, V.; Vajargah, S. H.; Nazar, L. F. A high-capacity and long-life aqueous rechargeable zinc battery using a metal oxide intercalation cathode. *Nat. Energy* **2016**, *1* (10), 16110
- (11) Zhang, L.; Chen, L.; Zhou, X.; Liu, Z. Towards High-Voltage Aqueous Metal-Ion Batteries Beyond 1.5 V: The Zinc/Zinc Hexacyanoferrate System. *Adv. Energy Mater.* **2015**, *5* (2), 1400930.
- (12) He, P.; Yan, M.; Zhang, G.; Sun, R.; Chen, L.; An, Q.; Mai, L. Layered VS₂ Nanosheet-Based Aqueous Zn Ion Battery Cathode. *Adv. Energy Mater.* **2017**, 7 (11), 1601920.
- (13) Lee, J.; Ju, J. B.; Cho, W. I.; Cho, B. W.; Oh, S. H. Todorokite-type $\rm MnO_2$ as a zinc-ion intercalating material. *Electrochim. Acta* **2013**, 112, 138–143.
- (14) Häupler, B.; Rössel, C.; Schwenke, A. M.; Winsberg, J.; Schmidt, D.; Wild, A.; Schubert, U. S. Aqueous zinc-organic polymer battery with a high rate performance and long lifetime. *NPG Asia Mater.* **2016**, 8 (7), e283–e283.
- (15) Ming, F.; Liang, H.; Lei, Y.; Kandambeth, S.; Eddaoudi, M.; Alshareef, H. N. Layered Mg_xV₂O₅·nH₂O as Cathode Material for High-Performance Aqueous Zinc Ion Batteries. *ACS Energy Lett.* **2018**, 3 (10), 2602–2609.
- (16) Alfaruqi, M. H.; Mathew, V.; Song, J.; Kim, S.; Islam, S.; Pham, D. T.; Jo, J.; Kim, S.; Baboo, J. P.; Xiu, Z.; Lee, K.-S.; Sun, Y.-K.; Kim, J. Electrochemical Zinc Intercalation in Lithium Vanadium Oxide: A High-Capacity Zinc-Ion Battery Cathode. *Chem. Mater.* **2017**, 29 (4), 1684–1694.
- (17) Xu, C.; Li, B.; Du, H.; Kang, F. Energetic zinc ion chemistry: the rechargeable zinc ion battery. *Angew. Chem., Int. Ed.* **2012**, *S1* (4), 933–935.
- (18) Trocoli, R.; La Mantia, F. An aqueous zinc-ion battery based on copper hexacyanoferrate. *ChemSusChem* **2015**, 8 (3), 481–485.
- (19) Li, G.; Yang, Z.; Jiang, Y.; Jin, C.; Huang, W.; Ding, X.; Huang, Y. Towards polyvalent ion batteries: A zinc-ion battery based on NASICON structured Na₃V₂(PO₄)₃. Nano Energy **2016**, 25, 211–217.
- (20) Li, W.; Wang, K.; Cheng, S.; Jiang, K. A long-life aqueous Znion battery based on $Na_3V_2(PO_4)_2F_3$ cathode. *Energy Storage Mater.* **2018**, *15*, 14–21.
- (21) Xia, C.; Guo, J.; Lei, Y.; Liang, H.; Zhao, C.; Alshareef, H. N. Rechargeable Aqueous Zinc-Ion Battery Based on Porous Framework Zinc Pyrovanadate Intercalation Cathode. *Adv. Mater.* **2018**, *30* (5), 1705580.
- (22) Xia, C.; Guo, J.; Li, P.; Zhang, X.; Alshareef, H. N. Highly Stable Aqueous Zinc-Ion Storage Using a Layered Calcium Vanadium Oxide Bronze Cathode. *Angew. Chem., Int. Ed.* **2018**, *57* (15), 3943–3948.

- (23) Jo, J. H.; Sun, Y.-K.; Myung, S.-T. Hollandite-type Al-doped $VO_{1.52}(OH)_{0.77}$ as a zinc ion insertion host material. *J. Mater. Chem. A* **2017**, 5 (18), 8367–8375.
- (24) Wan, F.; Zhang, L.; Dai, X.; Wang, X.; Niu, Z.; Chen, J. Aqueous rechargeable zinc/sodium vanadate batteries with enhanced performance from simultaneous insertion of dual carriers. *Nat. Commun.* **2018**, 9 (1), 1656.
- (25) Qu, Q.; Zhu, Y.; Gao, X.; Wu, Y. Core-Shell Structure of Polypyrrole Grown on V_2O_5 Nanoribbon as High Performance Anode Material for Supercapacitors. *Adv. Energy Mater.* **2012**, 2 (8), 950–955
- (26) Tang, W.; Gao, X.; Zhu, Y.; Yue, Y.; Shi, Y.; Wu, Y.; Zhu, K. A hybrid of V_2O_5 nanowires and MWCNTs coated with polypyrrole as an anode material for aqueous rechargeable lithium batteries with excellent cycling performance. *J. Mater. Chem.* **2012**, 22 (38), 20143–20145
- (27) Xu, D.; Wang, H.; Li, F.; Guan, Z.; Wang, R.; He, B.; Gong, Y.; Hu, X. Conformal Conducting Polymer Shells on V_2O_5 Nanosheet Arrays as a High-Rate and Stable Zinc-Ion Battery Cathode. *Adv. Mater. Interfaces* **2019**, 6 (2), 1801506.
- (28) Ahmed, B.; Xia, C.; Alshareef, H. N. Electrode surface engineering by atomic layer deposition: A promising pathway toward better energy storage. *Nano Today* **2016**, *11* (2), 250–271.
- (29) Wang, H.; Jia, G.; Guo, Y.; Zhang, Y.; Geng, H.; Xu, J.; Mai, W.; Yan, Q.; Fan, H. J. Atomic Layer Deposition of Amorphous TiO₂ on Carbon Nanotube Networks and Their Superior Li and Na Ion Storage Properties. *Adv. Mater. Interfaces* **2016**, 3 (21), 1600375.
- (30) Liu, J.; Li, X.; Cai, M.; Li, R.; Sun, X. Ultrathin atomic layer deposited ZrO_2 coating to enhance the electrochemical performance of $Li_4Ti_5O_{12}$ as an anode material. *Electrochim. Acta* **2013**, *93*, 195–201.
- (31) Yesibolati, N.; Shahid, M.; Chen, W.; Hedhili, M. N.; Reuter, M. C.; Ross, F. M.; Alshareef, H. N. SnO₂ anode surface passivation by atomic layer deposited HfO₂ improves Li-ion battery performance. *Small* **2014**, *10* (14), 2849–2858.
- (32) Zhi, J.; Yazdi, A. Z.; Valappil, G.; Haime, J.; Chen, P. Artificial solid electrolyte interphase for aqueous lithium energy storage systems. *Sci. Adv.* **2017**, 3 (9), No. e1701010.
- (33) Jung, Y. S.; Cavanagh, A. S.; Riley, L. A.; Kang, S. H.; Dillon, A. C.; Groner, M. D.; George, S. M.; Lee, S. H. Ultrathin direct atomic layer deposition on composite electrodes for highly durable and safe Li-ion batteries. *Adv. Mater.* **2010**, 22 (19), 2172–2176.
- (34) Ahmed, B.; Anjum, D. H.; Hedhili, M. N.; Alshareef, H. N. Mechanistic Insight into the Stability of HfO_2 -Coated MoS_2 Nanosheet Anodes for Sodium Ion Batteries. *Small* **2015**, *11* (34), 4341–4350.
- (35) Jiang, H.-q.; Endo, H.; Natori, H.; Nagai, M.; Kobayashi, K. Fabrication and efficient photocatalytic degradation of methylene blue over CuO/BiVO₄ composite under visible-light irradiation. *Mater. Res. Bull.* **2009**, 44 (3), 700–706.
- (36) Zhang, L.; Liu, M.; Ren, W.; Zhou, Z.; Dong, G.; Zhang, Y.; Peng, B.; Hao, X.; Wang, C.; Jiang, Z.-D.; Jing, W.; Ye, Z.-G. ALD preparation of high-k HfO₂ thin films with enhanced energy density and efficient electrostatic energy storage. *RSC Adv.* **2017**, 7 (14), 8388–8393.
- (37) Kim, H. S.; Cook, J. B.; Lin, H.; Ko, J. S.; Tolbert, S. H.; Ozolins, V.; Dunn, B. Oxygen vacancies enhance pseudocapacitive charge storage properties of MoO_{3-x}. *Nat. Mater.* **2017**, *16* (4), 454–460.
- (38) Augustyn, V.; Come, J.; Lowe, M. A.; Kim, J. W.; Taberna, P. L.; Tolbert, S. H.; Abruna, H. D.; Simon, P.; Dunn, B. High-rate electrochemical energy storage through Li⁺ intercalation pseudocapacitance. *Nat. Mater.* **2013**, *12* (6), 518–522.
- (39) Chamoun, M.; Brant, W. R.; Tai, C.-W.; Karlsson, G.; Noréus, D. Rechargeability of aqueous sulfate Zn/MnO₂ batteries enhanced by accessible Mn²⁺ ions. *Energy Storage Mater.* **2018**, *15*, 351–360.