

3M™ Adhesive Transfer Tape 9485PC

Last Revision Date: September, 2002



Product Description

Finite Element Analysis (FEA) data is available for this product at: [3m.com/FEA](https://www.3m.com/FEA)

This 3M™ Adhesive Transfer Tape with 3M™ Adhesive 350 is a modified acrylic adhesive ideal for very high-bond strength to many surfaces. It has excellent chemical resistance and bold strength even at elevated temperatures. This tape is offered with a fiber reinforced adhesive which is important for roll stability in narrow widths. Tapes using adhesive 350 are designed for temperature exposure to 450°F (232°C) for short periods of time and up to 300°F (149°C) over long time frames. This adhesive is a good choice for applications which require adhesion to Low Surface Energy plastics, powder coatings and oily metals.

General Information

- Excellent bond to metal and high surface energy plastics.
- Outstanding temperature and chemical resistance.
- Two adhesive thicknesses: 2 mil for thin profile labels and 5 mil for rougher surfaces.
- Available on various liners for specialized processing:
 - 55# Densified Kraft for rotary die-cutting
 - 62# Polycoated Kraft for steel rule die-cutting
 - 83# Polycoated Kraft for lay flat applications
 - 78# Extensible Kraft for conformable applications

Technical Information Note










The following technical information and data should be considered representative or typical only and should not be used for specification purposes.

Typical Physical Properties

Property	Values	Additional Information
Total Tape Thickness	0.127 mm (5 mil)	View
Test Method: ASTM D3652		
Total Tape Thickness	5 mil	View
Test Method: ASTM D3652		
Adhesive Type	Acrylic	
Liner	62# Polycoated Kraft	
Liner Print	None	


Liner Thickness	0.11 mm (4.2 mil)
Liner Thickness	4.2 mil
Dispenser Selection	For assistance in helping you determine the best dispenser for your application, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.

Typical Performance Characteristics

Property	Values	Additional Information
Short Term Temperature Resistance	232 °C (450 °F)	View 
Test Condition: Short Term (minutes, hour)		
Short Term Temperature Resistance	450 °F	View 
Test Condition: Short Term (minutes, hour)		
Long Term Temperature Resistance	121 °C (250 °F)	View 
Test Condition: Long Term (day, weeks)		
Long Term Temperature Resistance	250 °F	View 
Test Condition: Long Term (day, weeks)		
Minimum Long Term Temperature Resistance	-40 °C (-40 °F)	View 
Test Condition: Long Term (day, weeks)		
Minimum Long Term Temperature Resistance	-40 °F	View 
Test Condition: Long Term (day, weeks)		
Static Shear	10000 min	View 
Test Condition: 1000 g @ Room Temperature		
Notes: 1in x 1in size; test terminated after 10,000 minutes		
Static Shear	10000 min	View 
Test Condition: 500 g @ 70°C (158°F)		
Notes: 1in x 1in size; test terminated after 10,000 minutes		
Static Shear	10000 min	View 


Test Condition: 400 g @ 93°C (200°F)

Notes: 1in x 1in size; test terminated after 10,000 minutes

Static Shear 10000 min View 


Test Condition: 300 g @ 121°C (250°F)

Notes: 1in x 1in size; test terminated after 10,000 minutes

Static Shear 10000 min View 


Test Condition: 300 g @ 149°C (300°F)

Notes: 1in x 1in size; test terminated after 10,000 minutes

Static Shear 10000 min View 

Test Condition: 300 g @ 177°C (350°F)

Notes: 1in x 1in size; test terminated after 10,000 minutes

Static Shear 10000 min View 

Test Condition: 200 g load @ 232°C (450°F)

Notes: 1in x 1in size; test terminated after 10,000 minutes

180° Peel Adhesion 15.8 N/cm (145 oz/in) View 

Test Method: ASTM D3330

Dwell/Cure Time: 72

Dwell Time Units: hr


Temp C: 23C

Temp F: 72F

Environmental Condition: 50%RH

Substrate: Painted Metal

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion 145 oz/in View 

Test Method: ASTM D3330

Dwell/Cure Time: 72

Dwell Time Units: hr


Temp C: 23C

Temp F: 72F

Environmental Condition: 50%RH

Substrate: Painted Metal

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion 15.8 N/cm (145 oz/in) View 

Test Method: ASTM D3330

Dwell/Cure Time: 72

Dwell Time Units: hr


Temp C: 23C

Temp F: 72F

Environmental Condition: 50%RH

Substrate: Polycarbonate (PC)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion 145 oz/in View 


Test Method: ASTM D3330

Dwell/Cure Time: 72
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Polycarbonate (PC)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

13.6 N/cm (125 oz/in)

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Acrylic (PMMA)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

125 oz/in

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Acrylic (PMMA)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

13.1 N/cm (120 oz/in)

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Epoxy

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

120 oz/in

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Epoxy

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

9.3 N/cm (85 oz/in)

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: ABS

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

85 oz/in

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: ABS

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

9.8 N/cm (90 oz/in)

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polyvinyl chloride (PVC)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

90 oz/in

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polyvinyl chloride (PVC)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

8.7 N/cm (80 oz/in)

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polypropylene (PP)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

80 oz/in

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH
Substrate: Polypropylene (PP)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

15.8 N/cm (145 oz/in)


View 

Test Method: ASTM D3330

Dwell/Cure Time: 72
Dwell Time Units: hr
Temp C: 23C
Temp F: 72F
Environmental Condition: 50%RH

Substrate: Glass

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion	145 oz/in	View 
--------------------	-----------	--

Test Method: ASTM D3330

Dwell/Cure Time: 72

Dwell Time Units: hr

Temp C: 23C

Temp F: 72F

Environmental Condition: 50%RH

Substrate: Glass

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion	3.8 N/cm (35 oz/in)	View 
--------------------	---------------------	--

Test Method: ASTM D3330

Dwell/Cure Time: 72

Dwell Time Units: hr


Temp C: 23C

Temp F: 72F

Environmental Condition: 50%RH

Substrate: High Density Polyethylene (HDPE)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion	35 oz/in	View 
--------------------	----------	--

Test Method: ASTM D3330

Dwell/Cure Time: 72

Dwell Time Units: hr

Temp C: 23C

Temp F: 72F

Environmental Condition: 50%RH

Substrate: High Density Polyethylene (HDPE)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion	4.4 N/cm (40 oz/in)	View 
--------------------	---------------------	--

Test Method: ASTM D3330

Dwell/Cure Time: 72

Dwell Time Units: hr

Temp C: 23C

Temp F: 72F

Environmental Condition: 50%RH

Substrate: Low Density Polyethylene (LDPE)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion	40 oz/in	View 
--------------------	----------	--

Test Method: ASTM D3330

Dwell/Cure Time: 72

Dwell Time Units: hr

Temp C: 23C

Temp F: 72F

Environmental Condition: 50%RH

Substrate: Low Density Polyethylene (LDPE)

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion	10 N/cm (95 oz/in)	View 
--------------------	--------------------	--


Test Method: ASTM D3330

Dwell/Cure Time: 72
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Aluminum

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

95 oz/in

View 

Test Method: ASTM D3330

Dwell/Cure Time: 72
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Aluminum

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

16.4 N/cm (150 oz/in)

View 


Test Method: ASTM D3330

Dwell/Cure Time: 72
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Stainless Steel

Notes: 12 in/min (300 mm/min)

180° Peel Adhesion

150 oz/in

View 

Test Method: ASTM D3330


Dwell/Cure Time: 72
 Dwell Time Units: hr
 Temp C: 23C
 Temp F: 72F
 Environmental Condition: 50%RH
 Substrate: Stainless Steel










Notes: 12 in/min (300 mm/min)

Liner Release

44 g/in

Available Sizes

Property	Values	Additional Information
Note	Subject to Minimum Order Requirements	
Standard Roll Length	60 yd	
Maximum Length	54.9 m (60 yd)	View 
Width: 1/8 in to 3/8 in width		

Maximum Length	60 yd	View 
Width: 1/8 in to 3/8 in width		
Maximum Length	165 m (180 yd)	View 
Width: 3/8 in to 1/2 in width		
Maximum Length	180 yd	View 
Width: 3/8 in to 1/2 in width		
Maximum Length	329 m (360 yd)	View 
Width: 1/2 in to 1 in widths		
Maximum Length	360 yd	View 
Width: 1/2 in to 1 in widths		
Maximum Length	329 m (360 yd)	View 
Width: 1 in to maximum		
Maximum Length	360 yd	View 
Width: 1 in to maximum		
Maximum Available Width	48 in	
Normal Slitting Tolerance		
	± 0.8 mm (± 1/32 in)	
Normal Slitting Tolerance		
	± 1/32 in	
Core Size	76.2 mm (3 in)	View 
Test Name: ID		
Core Size	3 in	View 
Test Name: ID		

Storage and Shelf Life

Product retains its performance and properties for 24 months from date of manufacture if properly stored at room temperature conditions of 72°F (22°C) and 50% R.H. Storage in a plastic bag is recommended.

Handling/Application Information

Application Examples

Ideal adhesive application temperature range is 70°F to 100°F (21°C to 38°C). Initial application to surfaces at temperatures below 50°F (10°C) is not recommended for most pressure sensitive adhesives because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is satisfactory. For more specific information, contact our toll free 3M sales assistance number at 1-800-362-3550.

2 mil thick tapes may generally be used for joining materials that are relatively smooth, thin and have low residual stress. For materials with a rough or textured surface, the thicker adhesive film of the 5 mil tapes would be more appropriate for evaluation.

Application Techniques

For maximum bond strength the surface should be thoroughly cleaned and dried. Typical cleaning solvents are heptane or isopropyl alcohol. Consult manufacturer's Material Safety Data Sheet for proper handling and storage instructions. Bond strength can also be improved with firm application pressure and moderate heat (for metal surfaces only), from 100°F (38°C) to 130°F (54°C), causing the adhesive to develop intimate contact with the bonding surfaces.

References

Property	Values
3m.com Product Page	https://www.3m.com/3M/en_US/company-us/all-3m-products/~//3M-Adhesive-Transfer-Tape-9485PC/?N=5002385+3293241558&rt=rud
Safety Data Sheet SDS	https://www.3m.com/3M/en_US/company-us/SDS-search/results/?gsaAction=msdsSRA&msdsLocale=en_US&co=ptn&q=9485PC

ISO Statement

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001 standards.

Information

Technical Information: The technical information, guidance, and other statements contained in this document or otherwise provided by 3M are based upon records, tests, or experience that 3M believes to be reliable, but the accuracy, completeness, and representative nature of such information is not guaranteed. Such information is intended for people with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information. No license under any 3M or third party intellectual property rights is granted or implied with this information.

Product Selection and Use: Many factors beyond 3M's control and uniquely within user's knowledge and control can affect the use and performance of a 3M product in a particular application. As a result, customer is solely responsible for evaluating the product and determining whether it is appropriate and suitable for customer's application, including conducting a workplace hazard assessment and reviewing all applicable regulations and standards (e.g., OSHA, ANSI, etc.). Failure to properly evaluate, select, and use a 3M product and appropriate safety products, or to meet all applicable safety regulations, may result in injury, sickness, death, and/or harm to property.

Warranty, Limited Remedy, and Disclaimer: Unless a different warranty is specifically stated on the applicable 3M product packaging or product literature (in which case such warranty governs), 3M warrants that each 3M product meets the applicable 3M product specification at the time 3M ships the product. 3M MAKES NO OTHER WARRANTIES OR CONDITIONS, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OR CONDITION OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE, OR ARISING OUT OF A COURSE OF DEALING, CUSTOM, OR USAGE OF TRADE. If a 3M product does not conform to this warranty, then the sole and exclusive remedy is, at 3M's option, replacement of the 3M product or refund of the purchase price.

Limitation of Liability: Except for the limited remedy stated above, and except to the extent prohibited by law, 3M will not be liable for any loss or damage arising from or related to the 3M product, whether direct, indirect, special, incidental, or consequential (including, but not limited to, lost profits or business opportunity), regardless of the legal or equitable theory asserted, including, but not limited to, warranty, contract, negligence, or strict liability.

Disclaimer: 3M industrial and occupational products are intended, labeled, and packaged for sale to trained industrial and occupational customers for workplace use. Unless specifically stated otherwise on the applicable product packaging or literature, these products are not intended, labeled, or packaged for sale to or use by consumers (e.g., for home, personal, primary or secondary school, recreational/sporting, or other uses not described in the applicable product packaging or literature), and must be selected and used in compliance with applicable health and safety regulations and standards (e.g., U.S. OSHA, ANSI), as well as all product literature, user instructions, warnings, and limitations, and the user must take any action required under any recall, field action or other product use notice. Misuse of 3M industrial and occupational products may result in injury, sickness, or death. For help with product selection and use, consult your on-site safety professional, industrial hygienist, or other subject matter expert. For additional product information, visit www.3M.com.