
Model 6400

Features

- Simple Reliable Method
- Meets NACE MR0175 and MR0103
- Intrusive and Non-Intrusive Models
- No Chemicals or Shelf Life Problems

Introduction

Atomic hydrogen (H+), generated by the cathodic corrosion reaction can lead to two types of failures in steels; **Hydrogen Blistering** and **Hydrogen Induced Cracking** (HIC). Part of the hydrogen produced by the cathodic corrosion reaction may permeate the steel by diffusion, and the balance is dissolved in the process electrolyte or released as bubbles of gas. Poisoning agents in the process, such as hydrogen sulfide, cyanide, and arsenic, inhibit the formation of molecular hydrogen on the metal surface and therefore increase the proportion of atomic hydrogen which diffuses into steel.



HOLLOW PLUG A/F INSERT TYPE MODEL 6400

PATCH PROBE MODEL 6401 FIXED TYPE MODEL 6402

RETRACTABLE MODEL 6403

INTRUSIVE TYPES NON-INTRUSIVE TYPES

INTRUSIVE TYPES



HYDROGEN BLISTERING

Atomic (or nascent) hydrogen (H+), is small enough to permeate steel. At any cracks or inclusions in the pipes or vessels, the permeating atomic hydrogen combines to form hydrogen gas (H2) which is then too large to diffuse any further through the steel. The accumulation of hydrogen gas in these interstitial spaces results in an ever growing gas pressure causing a deformation known as blistering. The effects of blistering can be sufficient to rupture steel several inches thick. This phenomena occurs irrespective of the hardness of the steel.

HYDROGEN INDUCED CRACKING (HIC)

Hydrogen embrittlement, which can lead to hydrogen induced cracking, occurs in hard carbon steel (above HRC22) at areas of high stress. Atomic hydrogen permeating the steel collects at inclusions, lattice defects, and grain boundaries, causing the embrittlement and susceptibility to stress induced cracking and fatigue. Although the exact mechanism of hydrogen embrittlement is unknown, it has shown experimentally that it is correlated to the flux of atomic hydrogen into the steel.

HYDROGEN MONITORING

Hydrogen monitoring instruments indicate the susceptibility of steel to HIC and hydrogen blistering by measuring the rate of atomic hydrogen permeation. Generally, the utility of this application is in qualitatively detecting process upsets which tend to markedly increase the flux of nascent hydrogen. Because the hardness and stressing of the steel affects the

susceptibility to hydrogen damage, quantitative assessment is often difficult. However, relative hydrogen flow rates and the estimated associated damage they create are available (See Cosasco Application Note AN111 for further guidance). Hydrogen monitoring is also used on occasions to monitor the rate of corrosion, but the relationship between corrosion rate and hydrogen permeation varies with fluid dynamics, the method of hydrogen monitoring, and relative content of poisoning agents in the process.

Cosasco hydrogen probes detect hydrogen gas by the simple hydrogen pressure increase produced in an artificial cavity in the steel, i.e. the same mechanism as hydrogen blistering. The pressure build-up is directly proportional to the flux of atomic hydrogen, which can be determined by implementation of the ideal gas law. If the volume of the hydrogen probe cavity and the cross-sectional area across which diffusion is occurring is known, determination of the flux is a simple calculation.

Models 6400, 6401 and 6403 utilize the same bleed cross assembly (P/N 127130). The assembly consists of a bleed cross/block, pressure gauge (dual scale metric and english), thermometer (dual scale Celsius and fahrenheit), and bleed valve. The thermometer provides a means for correcting the change in pressure readings due to fluctuations in either ambient or process stream temperatures. The bleed valve is used to relieve built up pressures at intervals in order not to exceed the pressure gauge rating.

This reliable physical measurement principle is a simpler and easier method than other electrochemical methods. These alternative methods require the handling of hazardous chemicals, or have sealed cells with limited shelf life. The life of the intrusive probe type measurement elements are normally substantial but they may be replaced, when required. Several Cosasco hydrogen probe configurations are available, each having their own benefits and limitations.

MODEL 6400 HYDROGEN INSERT PROBE

Intrusive monitoring element which uses Cosasco Two Inch System Access Fitting.

Benefits

- Thin wall sensing element allows for quicker response times.
- Rated for pressures up to 6000 PSI
- Removable under system pressure.
- Internal temperature gauge allows compensation for temperature variations.

Limitations

Requires service valve and retriever if not already available

Spares	P/N
Bleed Cross Assembly	127130
Pressure Gauge 0 -100 psi	201924
Temperature Gauge	200746
Vent Valve	202008
O-Ring Seals	124603

MODEL 6401 HYDROGEN PATCH PROBE

Non-intrusive carbon steel patch welded to the exterior of the pipe or vessel to be monitored.

Benefits


- Directly monitors the flux of H+ through the walls of the pipe or vescel.
- Can be used at all system pressures and temperatures.
- Internal temperature gauge allows compensation for temperature variations.

Limitations

- Slower response time (dependent upon pipe or vessel wall thickness).
- Stress relieving after welding is necessary (possible problem for large vessels which are already installed).

Ordering Information

Note: For high velocity process conditions it is recommended that Wake Frequency Calculations be performed – please contact a Cosasco Representative for further details.



UNIT

WEIGHT: Model 6400

Probe length 5.75" - 9.75", 3 lbs./1.36 kg. Probe length 10.00" - 20.00", 4.5 lbs./2.04 kg. Probe length 21.00" - 30.00", 6 lbs./2.72 kg. Bleed Cross Assembly 2 lbs./.9 kg.

Ordering Information

Model	Hydroge	n Probe Assembly					
6401	Hydroge	Hydrogen Patch Probe					
	Code	Pipeline Size					
	02	2 Inches					
	03	3 Inches					
	04	4 Inches					
	06	6 Inches					
	08	8 Inches					
	10	10 Inches					
	12	12 Inches					
	14	14 Inches					
	16	16 Inches					
	18	18 Inches					
	20	20 Inches					
	24	24 Inches					
	30	30 Inches					
	36	36 Inches					
	FL	Flat					
		Code Material					
		G10220 AISI 1022 C.S.					
		K03011 ASTM A350 LF 2 C.S.					
		CODE Bleed Cross Assembly					
		0 Not Required					
		1 Supply – Not Installed					
		 					
6401 '	— 02 –	- G10220 — 1 ← Exampl					

UNIT WEIGHT: Model 6401 5 lbs./2.27 kg.

Bleed Cross Assembly 2 lbs./.9 kg

MODEL 6402 FIXED HYDROGEN PROBE

Intrusive monitoring element requiring 3/4" or 1" NPT fixed access

Benefits

- Low cost.
- Thin wall sensing element allows for quicker response times.

Limitations

- No compensation for temperature variations.
- Cannot be removed under system pressure.

Spares	P/N
Pressure Gauge (0-100 PSI)	201924
Vent Valve	202008

MODEL 6403 RETRACTABLE HYDROGEN INSERT PROBE

Intrusive monitoring element which requires a minimum of 1" full port valve and NPT mounting nipple for access.

Benefits

- Thin wall sensing element allows for quicker response times
- Retrievable under system pressure.
- Internal temperature gauge allows compensation for temperature variations.

Limitations

• Maximum pressure rating 1500 psi.

Spares	P/N
Bleed Cross Assembly	As Model 6400
Probe Insert P/N - Length	640011-LL
Stuffing Box	745002-8003

Note: For high velocity process conditions it is recommended to Wake Frequency Calculations be performed – please contact a Cosasco representative for further details.

Ordering Information

Note: For high velocity process conditions it is recommended that Drag Force Calculations be performed – please contact a Cosasco representative for further details.

Model Retrac			acta	able Hyd	rogen Probe			
	6403 Model 6				0 Hydro	gen Probe Assy. C/W Safety	/ Clamps	
			Co	de	Order L	ength in Inches		
	18		8	18 Inche	es			
			24		24 Inche	es		
			29	9	29 Inche	29 Inches		
					Code			
					0	Without Safety Clamp		
					1	With Safety Clamp		
	7	/	- 1	7		<u> </u>		
L	6403 — 18				1		Example	

UNIT WEIGHT: Model 6403

Probe Length 18" 7 lbs./3.17 kg. Probe Length 24" 8 lbs./3.60 kg. Probe Length 29" 9 lbs./4.08 kg. Bleed Cross Assembly 2 lbs./.9 kg.

Cosasco

11841 Smith Avenue Santa Fe Springs, CA 90670, USA Tel: 1-562-949-0123

Email: sales@cosasco.com
Web Site: www.cosasco.com

© Rohrback Cosasco Systems, Inc. All rights reserved

The contents of this publication are presented for information purposes only, and while effort has been made to ensure their accuracy, they are not to be construed as warranties or guarantees, express or implied, regarding the products or services described wherein or their use or applicability. We reserve the right to modify or improve the designs or specifications of our products at any time without notice.

Rohrback Cosasco Systems Corrosion Monitoring Equipment is manufactured and sold under one or more of the following US Patents: 4138878, 4238298, 4338563, 4514681, 4537071, 4587479, 4605626, 4625557, 4755744, 4839580, 4841787, 4882537 5243297

