



MOMENTIVE STO CURING AGENT

STO (stannous tin octoate) is the fastest of the commonly used curing agents and is especially useful where cure times of one hour or less are required.

One of several different curing agents available for two-component RTV silicone rubber compounds to provide a choice of cure speed, mixing ratio, or deep section cure.

Clear liquid

4 oz. (100ml) jar

Base is Silicone

Viscosity centipoise (cps) 250

