

Datasheet

____ Buff Linear Waterstruck Facing Brick



DE	TAI	11 C	FD.	\sim \sim \sim	DOP

Brick type / Category	U / 1					
Intended use	Bricks for use in unprotected masonry					
Geometry	G1	In accordance v	In accordance with EN1996-1-1.			
Dimensions, [mm]	ULT	Length 468	Width 108	Height 38		
Tolerance, [mm]	T1	Length ±9	Width ±4	Height ±2		
Range, [mm]	Rm	Length 15	Width 7	Height 4		
Gross density	1950	kg / m ³				
Tolerance	D1	±10%				
Compressive strength, average, min	60	N/mm ²				
Compressive strength, normalized, min	45	N/mm ²				
Water absorption, maximum	11	Weight%				
Durability against freeze/thaw	F2	Freeze/thaw re	esistant			
Active soluble salts content (Category)	S2					
Fire resistance	A1	contains < 1,0%	contains < 1,0% organic material			
SUPPLEMENTAL INFORMATION						
Initial rate of absorption, average value±tolerance	0,6 ± 0,5	kg/m ²				
Exposure class	MX4					
Bond strength	0,15	N/mm ² , table v	/alue, EN 998-2, ar	nnex C		
Bricks per m2 with a 12mm mortar joint	42	pcs / m ²	pcs / m ²			
Palletising	50	pcs	pcs			
Cleaning	Acid-cleaning is not allowed. See instructions for cleaning of masonry at randerstegl.com					
Mortar selection	The type of mortar is chosen on the basis of characteristics of strength and durability in accordance with static impacts and exposureclass.					
Brick is a natural material and variations can thus occur in terms of constructure. Therefore please see samples or reference buildings with the products in question.						