

Technical Data Sheet - European Standard

Stone type: Larvikite (Monzonite). Origin: Crafted by nature 300 million years ago in Larvik, Norway.

BEER & LUNDHS Night™

BEER & LUNDHS Night™ is the darkest stone in the Beer & Lundhs portfolio. The stone has a beautiful dark background with lustrous blue and silver crystals, and is an excellent choice for your ourdoor projects..

| Technical Properties | Test Surface | Standard | Unit | Mean | | |
|---|---------------|-----------------|-------------|-------|-------------|--|
| Apparent density | Sawn | NS-EN 1936 | kg/m³ | 2699 | ± | |
| Open porosity | Sawn | NS-EN 1936 | % | 0,45 | ± | |
| Water absorption | Sawn | NS-EN 13755 | % weight | 0,16 | ± | |
| Slip resistance | Sandblasted | NS-EN 14231 | SRV, dry | 89 | ± | |
| | Sandblasted | NS-EN 14231 | SRV, wet | 67 | ± | |
| | Sandwaterjet | NS-EN 14231 | SRV, dry | 95 | ± | |
| | Sandwaterjet | NS-EN 14231 | SRV, wet | 72 | ± | |
| | Flamed | NS-EN 14231 | SRV, dry | 92 | ± | |
| | Flamed | NS-EN 14231 | SRV, wet | 62 | ± | |
| | Bush hammered | NS-EN 14231 | SRV, dry | 91 | ± | |
| | Bush hammered | NS-EN 14231 | SRV, wet | 74 | ± | |
| Abrasion resistance – Capon, wide wheel | Sawn | NS-EN 14157 (A) | mm | 17,5 | ± | |
| Sound Velocity | Sawn | NS-EN 14579 | m/s | 5723 | ± | |
| Breaking load at dowel holes | Sawn | NS-EN 13364 | N | 4478 | ± | |
| Rupture energy | Sawn | NS-EN 14158 | J | 5,8 | ± | |
| Compressive strength | Sawn | NS-EN 1926 | MPa | 174,8 | ± | |
| Flexural strength | Sawn | NS-EN 12372 | MPa | 12,5 | ± | |
| Flexural strength after 56 freeze-/thaw cycles | Sawn | NS-EN 12371 | MPa | 13,3 | ± | |
| Flexural strength after 20 thermal shock cycles | Sawn | NS-EN 14066 | MPa | 12,2 | ± | |
| Frost resistance | | NS-EN 12371 | NS-EN 12371 | | | |
| Weight change | Sawn | NS-EN 12371 | % | -0,06 | ± | |
| Reduction in flexural strength | Sawn | NS-EN 12371 | % | 6,4 | | |
| Visual inspection | Sawn | NS-EN 12371 | Score 0-5 | 0 | (max value) | |
| Resistance to ageing by thermal shock | | NS-EN 14066 | NS-EN 14066 | | | |
| Weight change | Sawn | NS-EN 14066 | % | -0,02 | ± | |
| Reduction in flexural strength | Sawn | NS-EN 14066 | % | -2,4 | | |
| Visual inspection | Sawn | NS-EN 12371 | Score 0-5 | 0 | (max value) | |
| Petrographic composition ¹⁾ | | NS-EN 12407 | NS-EN 12407 | | | |

Tested at SINTEF 2019. The tests have been performed according to technical requirements given in e.g. NS-EN 1467 (rough blocks), NS-EN 1469 (slabs for cladding), NS-EN 12057 (modular tiles), NS-EN 12058 (slabs for floors and stairs).

BEER STEN AS

¹⁾ Test results are based on 3x2 cm objects and the examination provides information of the texture of the rock. However, variations in mineral composition and structure must be expected. Test results are an average of tests performed in 2006 and 2019. Only main minerals are listed.